

Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 1 094 346 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
**25.04.2001 Bulletin 2001/17**

(51) Int Cl.7: **G02B 6/255, G02B 6/26**

(21) Application number: **99308548.9**

(22) Date of filing: **28.10.1999**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE**  
Designated Extension States:  
**AL LT LV MK RO SI**

(30) Priority: **22.10.1999 IE 990889**

(71) Applicant: **Viveen Limited**  
**Co. Limerick (IE)**

(72) Inventors:  
• **O'Toole, Eamonn**  
**Co.Limerick (IE)**  
• **Davern, Timothy**  
**Co.Limerick (IE)**

- **Crowley, Michael**  
**Co.Limerick (IE)**
- **Hussey, Conleth Denis**  
**Co.Limerick (IE)**
- **O'Sullivan, Paul F.**  
**Castleroy,Co.Limerick (IE)**
- **Oakley, Kenneth Peter**  
**Castleroy,Co.Limerick (IE)**
- **O'Brien, Elaine**  
**National Technological Park Co Limerick (IE)**

(74) Representative: **Read, Matthew Charles et al**  
**Venner Shipley & Co.**  
**20 Little Britain**  
**London EC1A 7DH (GB)**

(54) **Fusion spliced optical fibers**

(57) Disclosed is a method for making an optical fiber fusion joint between two dissimilar single mode optical fibers (10,40) where the fibers have different core sizes and/or refractive index profiles due to different patterns of dopant. In one embodiment, one fiber is a standard step-index communication fiber, and the second fiber is a dispersion compensating fiber with a multiple layer refractive index profile. In a second embodiment, the

second fiber has a smaller core and a higher NA, up to about 0.3. A diffused dopant region, with a gradual longitudinal variation in diffusion extending over at least 3mm in each fiber, is formed adjacent to the splice. The diffusion of the various dopants in the second fiber tend to cause its refractive index profile to converge optically to that of the diffused step index communication fiber. As a consequence, the optical losses associated with the splice are relatively low.

## Description

[0001] The invention relates to the field of optical fiber systems involving connections between dissimilar optical fibers.

[0002] In addition to the standard communications fiber, a number of new types of optical fiber have been introduced into optical fiber based communication systems in recent years. Two groups of new fibres can be identified in terms of their refractive index distributions. The first group comprises dispersion controlling fibres with multiple layered refractive index profiles, while the second group comprises fibers that have a small core diameter but a high numerical aperture (NA) as compared with the standard communications fiber. The NA is defined as the square root of the difference between the squares of the refractive indices of the core and the cladding.

[0003] The standard communications single mode fiber is exemplified by the Corning product SMF 28 step index single mode fibre which consists of a circular core region of raised, approximately uniform, refractive index and a surrounding cladding region of uniform refractive index. The fiber consists of silica glass with the core doped with germania to give a raised refractive index and the cladding is typically undoped pure silica. The core diameter is about  $9.0\mu\text{m}$ , and the mode field diameter (MFD) is about  $10\mu\text{m}$  at the wavelength of  $1.55\mu\text{m}$  and the NA is about 0.1.

[0004] The dispersion controlling fiber (DCF) is exemplified by the Lucent Technologies DCF fiber which is used for dispersion compensation. This fiber has a multiple layered refractive index profile consisting of a raised refractive index core (doped with germania), surrounded by a ring layer of lowered refractive index (doped with fluorine), surrounded, in turn, by a slightly raised ring layer (doped with germania). The DCF fiber has a MFD of about  $5.0\mu\text{m}$  at the wavelength of  $1.55\mu\text{m}$ . The raising and lowering of the refractive index is with reference to the uniform silica cladding which surrounds the whole.

[0005] The high NA fibres are exemplified by the erbium doped fibre (e.g. Fibercore DF 1500F), the photo-sensitive fibre for Bragg grating writing (e.g. Fibercore PS1500) and the small core fibres used for pigtailed optoelectronic components (e.g. Fibercore SM1500).

[0006] In many potential applications, it is envisaged that these special optical fibers will be spliced permanently to standard communication fibers.

[0007] A standard method for connecting two lengths of standard communication fiber, referred to as fusion splicing, involves butting together the prepared ends of two fibers in the presence of a heat source e.g., a flame or electric arc such that the fiber ends melt and coalesce. Fusion splices are subject to optical losses, referred to collectively as "splice loss." Various factors have been identified as contributing to splice loss, including lateral offset of the cores, differences in the op-

tical characteristics of the mating fibers, and changes in the refractive index profile that take place during fusion.

[0008] When fibers having widely dissimilar mode field diameters (MFDs) and mode field shapes (MFSs) are spliced to one another, the mismatch of the mode fields at the location of the splice can result in high splice loss.

[0009] One technique for mitigating this contribution to the splice loss is described, for example, by D. B. Mortimore and J. V. Wright, "Low-Loss Joints between Dissimilar Fibers by Tapering Fusion Splices," *Electronics Letters*, 22 (13 Mar. 1986), pp. 318-319. This tapering technique involves first making a standard fusion splice and then drawing the softened glass in the vicinity of the splice such that the glass becomes constricted, decreasing the diameter of both the cladding and the core in the vicinity of the splice. This tapered region is said to function as a mode transformer that transforms the optical mode field of one fiber to that of the other with low optical loss. A standard communication fiber has reportedly been joined, with a total splice loss of 0.56 dB, to a fiber having a core diameter of  $3.8\mu\text{m}$  and an MFD of  $4.34\mu\text{m}$ . This tapering by drawing approach has never been practically demonstrated outside the laboratory.

[0010] An alternative approach to fusion splicing of fibers, based on the diffusion of dopants in the refractive index profile, was reported by, for example, W. Zell, et al., "Low-Loss Fusion Splicing of PCVD-DFSM Fibers," *Journal of Lightwave Technology*, LT-5, (September 1987), pp. 1192-1195. The approach of Zell, et al. involves spreading the smaller of the cores of the (not very dissimilar) mating fibers by diffusing the index-raising dopant during an annealing step after the splice is formed. (The index-lowering dopant of the cladding was also found to diffuse during heating.) Zell, et al. reported that diffusion tapering was effective in reducing the optical loss in a fusion splice between a depressed cladding, single-mode (DCSM) fiber and a dispersion flattened, single-mode (DFSM) fiber having a smaller MFD than the DCSM fiber.

[0011] Significantly, the heat treatment, reported in that work, caused the concentrations of germanium and fluorine dopants, respectively, to exhibit a diffusion profile extending axially from the joint. At a wavelength of  $1.3\mu\text{m}$ , a splice loss of 0.30 dB was achieved by Zell, et al. This splice loss was smaller than the theoretical loss in a step joint between the two fibers, and the difference was attributed to diffusion tapering. However, at a wavelength of  $1.55\mu\text{m}$ , a somewhat greater loss, 0.35 dB, was observed, and no reduction of loss attributable to diffusion tapering was observed.

[0012] In a practical communication system, it is desirable for splices between different fibers to exhibit still smaller losses, e.g., losses much smaller than 0.3 dB. The Zell, et al. reference does not disclose a technique that can produce low-loss splices between fibers having drastically different core sizes, refractive index profiles,

MFDs and MFSs. Indeed, at 1.55  $\mu\text{m}$ , which corresponds approximately to the operating wavelength of erbium amplifiers, Zell, et al. has failed to show any improvement in splice loss by diffusion tapering. Moreover, the improved splice reported there involved a pair of only moderately dissimilar fibers both with relatively large cores, i.e., fibers with respective MFDs of 10.1  $\mu\text{m}$  and 7.6  $\mu\text{m}$  at a wavelength of 1.55  $\mu\text{m}$ .

**[0013]** The work of Zell et al. has been extended by Cohen et al. ('Optical communications system comprising a fiber amplifier' US Patent 5,074,633 Dec 24, 1991). Cohen et al. describes a splice joint with a loss of less than 0.15 dB at 1.55  $\mu\text{m}$  between an erbium doped fiber with a MFD of less than 4  $\mu\text{m}$  and a communications fiber with a MFD of about 10  $\mu\text{m}$ . This result was also achieved with an annealing step after the splice was formed where the heat source was an oxy-hydrogen flame of about 0.6 mm in length.

**[0014]** Zell and Cohen each use diffusion tapering to a limited extent by preferentially diffusing the smaller of the cores at the annealing stage and keeping the diffusion of the larger of the cores to a minimum in an effort to equalise the core diameters. Thus, the diffusion takes place primarily in one fiber only. Cohen uses a maximum diffusion time of only 200 seconds at 2000 °C.

**[0015]** The difference in MFD and MFS between DCF and standard communications fiber is very large compared to the difference in fibers which have been spliced using the prior art. Thus, practitioners in the art have until now failed to provide a fusion splice that is capable, for operation at about 1.55  $\mu\text{m}$ , of joining a multiple layer fiber to a communications fiber having radically different MFDs and MFSs, with a total splice loss less than 0.2 dB over a wide wavelength range. Similarly, splice losses between the standard communications fibre and high NA fibres have not been demonstrated below about 0.13 dB.

**[0016]** The present invention provides an improved annealed optical fiber joint between first and second doped optical fibers fusion spliced to one another, having different core sizes and different refractive index profiles. According to the invention, a longitudinal diffused region is associated with the splice, comprising a length of both fibers, wherein the amount of diffusion increases as the splice is approached along each fiber, the length of the diffused region in each fiber being 3 mm or more; and the fusion splice has a total splice loss, over the range of signal wavelengths, of less than 0.2dB.

**[0017]** The length of the diffused region in each fiber may be approximately 5mm and the provision of a substantial diffused region in both fibers gives rise to a reduction in splice loss according to the invention.

**[0018]** The invention also includes a method of annealing an optical fiber joint between first and second optical fibers fusion spliced to one another for operation in a predetermined wavelength range, the second fiber having a different core size and different refractive index profile from the first fiber, characterised by heating the

fibers in the region of the fusion splice to produce diffusion of dopants therein to form a longitudinal diffused region comprising a length of both fibers wherein the amount of diffusion increases as the splice is approached along each fiber, the length of the diffused region in each fiber being 3 mm or more; and the fusion splice has a total splice loss, over the range of signal wavelengths, of less than 0.2dB.

**[0019]** According to the invention, the cores of the two fibers are both diffused substantially to reduce splice loss. The amount of diffusion in each of the fibers is much greater than in the aforementioned prior art. The diffusion times may be much longer, for example 3 to 30 minutes at a peak temperature of 2000°C. The method according to the invention causes dopant diffusion in both of the fibers. However, for a good optical match at the joint is not necessary for the extent of the diffusion to be total. Indeed, a modest increase in the extent of the diffusion over that demonstrated in the prior art, provided that both fibers are exposed nearly equally to the diffusing heat source, can improve the joint losses considerably compared to the prior art.

**[0020]** In one embodiment, one fiber is a standard step-index communication fiber, and the second fiber is a multilayered dispersion compensating fiber (DCF). A diffused dopant region is included adjacent the splice. The diameter of the communications fiber core increases gradually within the diffusion region as the splice joint is approached along this fiber. The diffusion of the various dopants in the DCF fiber also increases gradually as the splice joint is approached along this fibre. At the splice joint the diffusion of these dopants tend to cause the refractive index profile to converge optically to that of the diffused step index communications fiber. As a consequence of the diffusion region and its gradual longitudinal variation, the optical losses associated with the splice are relatively low, i.e. less than 0.2dB at the operating wavelength, even when there is relatively high mismatch between the mode field diameters and mode field shapes (at a signal wavelength) in the respective fibers.

**[0021]** In a second embodiment, one fiber is a standard step-index communication fiber, and the second fiber is a high NA fibre with a NA of 0.3. A diffused dopant region is included adjacent the splice. The diameter of both fiber cores increase gradually within the diffusion region as the splice joint is approached along the fibers. The diffusion of the core in the high NA fiber tends to cause it to converge optically to that of the diffused step index communications fiber. As a consequence of the diffusion region and its gradual longitudinal variation, the optical losses associated with the splice are relatively low i.e. less than 0.1dB, even when there is relatively high mismatch between the mode field diameters (at a signal wavelength) in the respective fibers.

**[0022]** In order that the invention may be more fully understood, embodiments thereof will now be described by way of example with reference to the accompanying

drawings wherein:

FIG. 1(a) is a schematic representation, not to scale, of a pair of dissimilar optical fibers to be joined,

FIG 1(b) is a schematic representation of the refractive index profiles of the two fibers,

FIG. 2 is a schematic representation, not to scale, of a pair of dissimilar fibers joined by a fusion splice with diffusion of the refractive index on both sides of the splice,

FIG. 3 is a schematic of the fiber holding mechanism of the heat treatment rig, and

FIG.4 is a drawing of a suitable burner head and a configuration for testing for splice loss.

[0023] The splice joint between unlike fibres is clearly an abrupt transition in the optical path and can be a major source of loss for the propagating light. Radial and longitudinal diffusion of the dopants from the core regions can, from the point of view of the optical signal, smooth out the transition and reduce the losses at the joint. The greater the extent of diffusion the smoother is the optical transition and the less is the loss experienced at the joint. However care must be taken to ensure that the boundary between the diffused region and the undiffused region in each fiber does not itself create an abrupt transition in the optical path.

[0024] For any longitudinal transition in an optical waveguide there is an allowed transition rate, which will guarantee low loss for light passing through the transition. This allowed transition rate is governed by the so-called Adiabatic Criterion, which is well known to those skilled in the art (see, for example, W.J. Stewart and J. D. Love, "Design limitations on tapers and couplers in single mode fibres" ECOC 1985 pp. 559-562). For the present purposes, it is sufficient to note that the longitudinal profiles of the diffused core regions need to be controlled during the diffusion process so that the appropriate transition rate for each fiber is achieved.

[0025] Diffusion of the dopants in the fibre can be achieved by heating the fiber. The extent of diffusion is proportional to the heating temperature and heating time.

[0026] The simplest implementation of a gradual transition in the amount of diffusion along a length of optical fiber is to exploit the temperature gradient of a gas flame and to ensure that the flame is long enough that an appropriate transition rate is achieved about the splice point. More diffusion will occur at the centre of the flame where the fiber is hottest, and less and less diffusion occurs on moving out to the edge of the flame. A more elaborate approach for such a diffusion regime is to introduce a longitudinal back and forth motion to the diffusing flame, i.e. the flame can be made to oscillate over a length of the fiber. The amplitude of the oscillation can be varied during the diffusion process such that different regions of the fiber have different exposure times to the

flame. Since the amount of diffusion depends on heating time, more diffusion will occur where the fiber is heated for the longest time.

[0027] In the prior art, where the fibers are heated with an electric arc, the extent of the heated region is about 1 to 2 mm. Any diffusion of the fiber core in such an arc will have a relatively abrupt transition. While this may be adequate for improving some fiber splice joints where a low extent of diffusion is required, it is not adequate for joints where the difference between the two fibers is considerable. In accordance with the invention, the length of the hot zone is increased and the fiber temperature is suitably graded within the hot zone, so that a suitable diffusion profile can be achieved.

[0028] It is accordingly possible to improve the joint loss between two fibers by lengthening and suitably grading the diffusion about the splice point. On examining the adiabatic criterion for different fiber types, it is found that different fiber types require different gradations of diffusion to achieve low loss. High NA matched cladding fibers can tolerate the fastest diffusion transition rates, the standard low NA matched cladding communications fibers require a slower transition rate, and the multiple layer fibers incorporating a depressed cladding layer need the slowest rate of all. Ideally the fibers on each side of the splice should be heat treated differently to achieve the lowest loss in the shortest possible length. However, in practice, it is convenient to heat treat both fibers according to the requirements of the slowest fiber type. A single flame with a graded temperature distribution about its centre is a suitable exemplary embodiment of this, which can be used to achieve greater diffusion in both fibers over a longer length of both of them as compared with Cohen *supra*.

[0029] For illustrative purposes, a preferred embodiment of the invention as applied to DCF fiber will now be described although it will be appreciated that the principles of the invention can be applied to other fiber types.

[0030] With reference to FIG. 1, two fibers that are to be spliced together are shown. The splice is to be formed between first and second fibers 10 and 40. The fiber 10 comprises a DCF fiber. Fiber 10 includes a uniform cladding 20 and series of layers constituting a refractive index profile with raised inner core 30. The second fiber 40 is not a DCF fiber, and is typically an optical communication fiber. Fiber 40 includes a cladding 50 and a core 60. Fibers 10 and 40 are typically single mode fibers.

[0031] Cladding 20 of the DCF fiber exemplarily comprises silica glass doped with germania for the inner high refractive index raised core, doped with typically fluorine in the lowered refractive index ring 70 surrounding the core, with yet another slightly raised germania doped ring 80 surrounding that, surrounded finally with the uniform cladding 20. The outer diameter of cladding 20 is advantageously the same as the outer diameter of cladding 50. If fiber 40 is a standard optical communication fiber, then this outer diameter is generally about 125  $\mu\text{m}$ .



[0032] Turning now to FIG. 2, fibers 10 and 40 are joined by a fusion splice 90. It is desirable for the total splice loss associated with splice 90 to be less than 0.3 dB over a wide wavelength range (160 nm.) centred on 1.55  $\mu\text{m}$ .

[0033] For illustrative purposes, a procedure for making annealed and hence diffused fusion splices in accordance with the invention is described below. Splice losses less than 0.2 dB, and as low as about 0.15 dB, have been achieved by using this procedure to join standard communication fibers (SMF28) to Lucent DCF fibers.

[0034] In accordance with the illustrative procedure, the respective ends of fibers 10 and 40 that are to be joined are first prepared and then assembled in a conventional fusion splicing apparatus. Fusion splicing apparatuses using, e.g., flames, electric arcs, or tungsten filaments as heat sources are well known in the art and are readily commercially available. One suitable example of fusion splicing machine is the Model 30S manufactured by Fujikura Corporation.

[0035] Techniques of end preparation are well known in the art. By the use of such techniques, each of the ends to be joined is desirably cleaved such that it is inclined no more than 1 degree from a plane perpendicular to the longitudinal axis of the fiber. After the ends are prepared, the fibers are mounted and aligned in the splicing apparatus and spliced using best practice for the particular machine being used.

[0036] The spliced fiber is then removed from the splicing machine and mounted in a heat treating rig such that the fibre is suspended between two aligned platforms 100 with the splice point 90 lying midway between them as illustrated in Figure 3. A hydrogen torch is then introduced to the splice joint region. The torch head 110, typically made from ceramic or stainless steel, is introduced so that the gas flows vertically downwards onto the fibres. With reference to Figure 4, the nozzle of the burner is about 8mm diameter with a rim thickness of about 1mm. The envelope of gas flame has an inverted dome shape 120. The torch height and the gas flow rates are adjusted to ensure that the fibre lies at a tangent to the flame and a length of about 10mm of fibre is glowing in the flame, disposed symmetrically about the splice point 90 i.e.

[0037] with about 5mm in each of the fibers 10, 40. The gas flow rates can range from 100 to 400 ccm/min and is typically 300 ccm/min.

[0038] The heat treatment involves the heating of the splice region i.e., over a length of about 10 mm, as previously described, to a certain temperature and temperature gradient, and maintaining the splice region at that temperature distribution for a temperature-dependent time. Diffusion of dopants occurs during the heat treatment and the longitudinal gradient in diffusion mirrors that of the heat gradient of the flame. As a result, with reference to FIG. 2, the cores of fiber 40, and refractive index distributions of fiber 10, both diffuse gradually

more and more to form a dopant diffused region 75 along the heated region to such an extent that the optical distinctions between the fibers at the splice point 90 get blurred. Provided that optical guidance is maintained in the diffused region, the propagating light can traverse the splice with little or no loss.

[0039] Generally, it has been found according to the invention that an improved standard fiber/DCF fibre splice can be produced when the annealing takes place with a flame over a fiber length of 6 - 20mm with at least a length of 3mm of each fiber being heated in region of the joint. Thus between 3-10mm of each fiber is subject to the flame to produce the longitudinal dopant diffused region 75 shown in Figure 2 wherein the amount of diffusion increases as the splice is approached along each fiber. Conveniently, the diffused region is produced in approximately 5mm of each fiber 10, 40. The splice is heated to a temperature within a range of 1700 - 2000°C for a time in a range of 3, 4 or 5 to 30 minutes. The resulting annealed joint between the fibers exhibit improved loss characteristics of less than 0.2 dB and typically in a range of 0.15 - 0.2 dB. The conditions are determined empirically for the actual fiber types used such as to provide diffusion in the fibers that results in the aforementioned adiabatic criterion being established in the transition between the cores of the spliced fibers.

[0040] The annealing technique just described can also be used with advantage for a fusion splice between standard telecommunications single mode fiber and a high NA fiber. Using the aforementioned conditions for the improved standard fiber/DCF fibre splice, the heating of the splice similarly produces a longitudinal dopant diffused region wherein the amount of diffusion increases as the splice is approached along each fiber. The resulting splice loss is less than 0.1 dB. The high NA fiber may have a value of NA greater than 0.1 and as high as 0.4. A typical value of NA is 0.3.

[0041] During the heat treatment, the throughput optical power of the splice may be monitored by a conventional technique, such as with an optical loss test set comprising a light source 130 and an optical power meter 140 shown in Figure 4. It is generally observed that the power, detected by the power meter, continues to increase and eventually reaches saturation at a maximum value. Thus, an optimum heating time can readily be identified at a given temperature, such that the transmitted power is maximised when the peak temperature is maintained for that optimum time period. So, once the heating conditions are set, the need for optical monitoring is eliminated from the procedure.

#### Example 1

[0042] A Lucent DCF single-mode fiber (Fiber type DK-SM) and a single-mode communication fiber (Corning SMF28) were joined by a fusion splice with extended heat treatment to cause diffusion.

[0043] The DCF fiber had an outer diameter of 125

$\mu\text{m}$  and a MFD of about  $5.0\ \mu\text{m}$ . The communication fiber had an outer diameter of  $125\ \mu\text{m}$  and a MFD of about  $10\ \mu\text{m}$ . The fiber ends to be joined were prepared as described above, aligned and spliced in a conventional fusion splicing apparatus.

[0044] The optical power transmitted across the fiber joint was monitored by means of the laser light source 130 coupled to the fiber 40 and the optical detector 140 coupled to the fiber 10. A combined length of about 10 mm, centred on the splice 90, was heated with a hydrogen flame. The torch had a ceramic head with an 8 mm aperture. The height was adjusted to produce a hot zone length of 10 mm on the fiber at a maximum temperature of  $1700 - 2000^\circ\text{C}$ . A hydrogen gas flow at a rate of about 300 cc/minute passed through the aperture.

[0045] The splice region was heated to the peak temperature, and maintained at that temperature for a time period of about 10 mins, at which point the maximum power transmission was observed. The resulting splice loss averaged over ten samples at a wavelength of  $1.55\ \mu\text{m}$  was 0.17 dB, with a standard deviation of 0.03 dB.

## Example 2

[0046] A Fibrecore High NA ( $\text{NA}=0.3$ ) single-mode fiber (PS1500) manufactured by Fibercore plc of Southampton GB and a single-mode communication fiber (Corning SMF28) were joined by a fusion splice with extended heat treatment to cause diffusion.

[0047] The High NA fiber had an outer diameter of  $125\ \mu\text{m}$  and a MFD of about  $4.0\ \mu\text{m}$ . The communication fiber had an outer diameter of  $125\ \mu\text{m}$  and a MFD of about  $10\ \mu\text{m}$ .

[0048] The fiber ends to be joined were prepared as described above, aligned and spliced in the conventional fusion splicing apparatus.

[0049] The optical power transmitted across the fiber joint was monitored by a conventional technique. A combined length of about 10 mm, centred on the contact point, was heated with a hydrogen flame. The torch had a ceramic head with an 8 mm aperture. The height was adjusted to produce a hot zone length of 10 mm on the fiber. A hydrogen gas flow at a rate of about 200 cc/minute passed through the aperture.

[0050] The splice region was heated to a peak temperature of  $1700 - 2000^\circ\text{C}$  and maintained at that temperature for a time period of about 5 mins, at which point the maximum power transmission was observed. The resulting splice loss averaged over ten samples at a wavelength of  $1.55\ \mu\text{m}$  was 0.05 dB, with a standard deviation of 0.01 dB.

[0051] Many modifications and variations fall within the scope of the invention. For example, different types of DCF fibers may be used instead of the Lucent fiber previously described and different types of high NA fibers can be used. Also, the invention has application to splices between other dissimilar fibers to reduce the splice loss.

## Claims

1. An annealed optical fiber joint comprising first and second doped optical fibers (10,40) fusion spliced to one another for operation in a predetermined wavelength range, the second fiber having a different core size and different refractive index profile from the first fiber, **characterised in that** associated with the fusion splice (90) is a longitudinal diffused region (75) comprising a length of both fibers wherein the amount of diffusion increases as the splice is approached along each fiber, the length of the diffused region in each fiber being 3 mm or more; and the fusion splice has a total splice loss, over the range of signal wavelengths, of less than 0.2 dB.
2. A joint according to claim 1 wherein the first fiber comprises a standard telecommunications single mode fiber (40) and the second fiber comprises a DCF fiber (10).
3. A joint according to claim 2 wherein the DCF fiber comprises a core (30) surrounded by an outer cladding, the core having a higher refractive index than the cladding, and a dispersion compensation region (70,80) between the core and outer cladding.
4. A joint according to claim 1 wherein the first fiber comprises a standard telecommunications single mode fiber and the second fiber has a value of NA which is higher fiber than that of the first fiber.
5. A joint according to claim 3 wherein the second fiber has a value of NA approximately equal to 0.3.
6. A joint according to claim 4 or 5 wherein the second fiber has an erbium doped core.
7. A joint according to any one of claims 3 to 6 wherein the splice loss is less than 0.1dB.
8. A joint according to any preceding claim wherein the first fiber has a core diameter in a range of  $8 - 11\ \mu\text{m}$  and the second fiber has a core diameter in a range of  $2 - 8\ \mu\text{m}$ .
9. A joint according to any preceding claim wherein the length of the diffused region is less than 10mm in each fiber.
10. A joint according to any preceding claim wherein the length of the diffused region is approximately 5mm in each fiber.
11. A method of annealing an optical fiber joint between first and second optical fibers (10,40) fusion spliced to one another for operation in a predetermined

wavelength range, the second fiber having a different core size and different refractive index profile from the first fiber, **characterised by** heating the fibers in the region of the fusion splice to produce diffusion of dopants therein to form a longitudinal diffused region (75) comprising a length of both fibers wherein the amount of diffusion increases as the splice is approached along each fiber, the length of the diffused region in each fiber being 3 mm or more; and the fusion splice has a total splice loss, over the range of signal wavelengths, of less than 0.2dB.

12. A method according to claim 11 including carrying out the heating of the fibers with a gas flame.
13. A method according to claim 11 or 12 wherein the heating of the fibers is carried out to a peak temperature between 1700 °C and 2000 °C.
14. A method according to claim 11, 12 or 13 wherein the heating is carried out for between 3 and 30 minutes.
15. A method according to any one of claims 11 to 14 including monitoring optical splice loss for the fusion splice whilst carrying out the heating, and ceasing the heating when the splice loss reduces to a particular level.
16. A method according to any one of claims 11 to 15 wherein the heating is carried out with a gas torch.
17. A method according to claim 16 wherein the torch burns hydrogen and including controlling the flow of hydrogen to the torch to be between 100 and 400 cc/min.
18. A method according to claim 16 or 17 including oscillating the torch along the fibers to produce a maximum temperature at the splice and a temperature gradation therefrom along the fibers.
19. A method according to any one of claims 11 to 18 including producing the splice between a standard telecommunications fiber and a DCF fiber.
20. A method according to any one of claims 11 to 18 including producing the splice between a standard telecommunications fiber and a high NA fiber.
21. An annealed optical fiber joint produced by a method as claimed in any one of claims 11 to 20.
22. An annealed optical fiber joint according to any one of claims 1 to 10 or 21 configured for operation in a wavelength range centred on 1.55  $\mu\text{m}$ .




Fig. 1a




Fig. 1b






Fig. 2




Fig. 3




Fig. 4



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 99 30 8548

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
D, X	US 5 074 633 A (KRAUSE JOHN T ET AL) 24 December 1991 (1991-12-24)  * column 4, line 14 - column 5, line 68; figures 1,2 *	1,4-9, 11-18, 20-22	G02B6/255 G02B6/26
A	---	2,3,19	
A	EP 0 340 042 A (BRITISH TELECOMM) 2 November 1989 (1989-11-02) * column 2, line 10 - column 3, line 13 *	1,11	
A	TEWARI R ET AL: "Modified figure of merit for dispersion compensated optical fibres" OPTICS COMMUNICATIONS, NL, NORTH-HOLLAND PUBLISHING CO. AMSTERDAM, vol. 155, no. 4-6, 15 October 1998 (1998-10-15), pages 260-262, XP004146449 ISSN: 0030-4018 * the whole document *	2,19	
A	EP 0 890 853 A (ERICSSON TELEFON AB L M) 13 January 1999 (1999-01-13) * page 3, line 40 - page 4, line 16 *	1,11	TECHNICAL FIELDS SEARCHED (Int.Cl.7)  G02B
A	PATENT ABSTRACTS OF JAPAN vol. 015, no. 344 (P-1245), 30 August 1991 (1991-08-30) & JP 03 130705 A (NIPPON TELEGR & TELEPH CORP), 4 June 1991 (1991-06-04) * abstract; figure 2 *	1,11	
The present search report has been drawn up for all claims			
Place of search <b>MUNICH</b>		Date of completion of the search <b>20 November 2000</b>	Examiner <b>Lord, R</b>
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- &amp; : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/82 (F04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 30 8548

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.  
The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

20-11-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5074633 A	24-12-1991	DE 69107723 D	06-04-1995
		DE 69107723 T	29-06-1995
		EP 0469792 A	05-02-1992
		JP 4253003 A	08-09-1992
EP 0340042 A	02-11-1989	AT 82561 T	15-12-1992
		AU 629214 B	01-10-1992
		AU 3571189 A	24-11-1989
		CA 1317803 A	18-05-1993
		DE 68903528 D	24-12-1992
		DE 68903528 T	01-07-1993
		ES 2036029 T	01-05-1993
		WO 8910332 A	02-11-1989
		HK 129496 A	26-07-1996
		JP 2911932 B	28-06-1999
		JP 3504052 T	05-09-1991
		US 5142603 A	25-08-1992
EP 0890853 A	13-01-1999	SE 511966 C	20-12-1999
		JP 11072645 A	16-03-1999
		SE 9702211 A	10-12-1998
		US 6062743 A	16-05-2000
JP 03130705 A	04-06-1991	JP 2618500 B	11-06-1997

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82